

DESIGN: CELIA

BASIC INFORMATION

Number of colour ways	4	Tariff item number	5515998000
MID	INDDEEXP16	Country of origin	India
Characteristics	Sheer	Vertical repeat cm	Plain
Vertical repeat inch	Plain	Horizontal repeat cm	Plain
Horizontal repeat inch	Plain	Double folded face in	Yes
Full roll diameter cm	21	Full roll diameter inch	8.27
Average piece length m	50	Minimum for special colour m	1000
Delivery time weeks special lab dip	4	Railroaded	Yes

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains	Yes	Curtains and draperies	Yes
----------	-----	------------------------	-----

ENVIRONMENTAL STANDARDS



GRS post-consumer



STANDARD 100
2111232
Centexbel



Yes



Prop 65

Yes

FR STANDARDS

FMVSS 302 Pass

No

DESIGN: CELIA

FABRIC SPECIFICATIONS

Composition	48% Recycled Polyester, 29% Linen, 23% Organic Cotton	Average yarn number	25.35
Construction	12.5x16.4	Woven	Yes
Useable width cm	3.04	Useable width inch	119.69
Full width cm	306	Full width inch	120.47
Weight g/m ²	114	Thickness mm	0.300
Colouring type	Yarn dyed	Filament or staple	100% staple
Textured or non textured	100% not textured		

Treatment

No treatment	Yes
--------------	-----

Type of finish

Stenter	Yes
---------	-----

Type of print or dye

Disperse	Yes	Reactive	Yes
----------	-----	----------	-----

Weaving type

Dobby	Yes
-------	-----

FABRIC TYPE

There are no technical details for this section.

DESIGN: CELIA

MECHANICAL PERFORMANCE

Colour fastness to light	7		
Colour fastness to light - ISO 105-B02			
Colour fastness to light	7		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	57	Tearing strength weft N	78
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	390	Tensile strength weft N/5cm	300
Elongation - ISO 13934-1			
Elongation warp %	22.5	Elongation weft %	16.5
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.12	Dimensional change warp after ironing with steam	-0.20
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	0.00
Dimensional change weft after ironing with steam	0.00	Dimensional change weft after ironing without steam	0.13

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330			
Dimensional change warp	-0.27	Dimensional change warp after ironing	-0.40
Dimensional change weft	-1.13	Dimensional change weft after ironing	1.13
Colour fastness ISO 105 C06	4-5		
Resistance to domestic washing 60°C, indicated in % - ISO 6330			
Dimensional change warp	-0.96	Dimensional change warp after ironing	-0.93
Dimensional change weft	-2.05	Dimensional change weft after ironing	-1.99
Colour fastness ISO 105 C06	4-5		
Resistance to dry cleaning P, indicated in % - ISO 105 D01			
Dimensional change warp	-0.86	Dimensional change warp after ironing	-0.46
Dimensional change weft	-0.43	Dimensional change weft after ironing	-0.46
Colour fastness ISO 105 D01	4-5		

DESIGN: CELIA

CONSTRUCTION

Yarn 1

Warp Composition	66% Recycled Polyester, 34% Organic Cotton	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	2/36's
Warp Threads per cm	12.5	Warp TPM	460

Yarn 2

Weft Composition	100% Linen	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	44/1
Weft Threads per cm	8.2	Weft TPM	400

Yarn 3

Weft Composition	66% Recycled Polyester, 34% Organic Cotton	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Is Textured	Yes
Weft Sizes	2/36's	Weft Textured	Yes
Weft Threads per cm	8.2	Weft TPM	460

DOWNLOADS / CERTIFICATES

There are no technical details for this section.