

TECHNICAL FABRIC DETAILS

MUNA


Muna is a heavyweight fabric with a pleasant touch designed for outdoor use. Perfect for upholstery, this irregularly designed fabric creates unique effects, with light and neutral tones to emphasize elegance and detail. Add a special touch to any space, indoors or out.



Article specification

Width	160 cm
Horizontal repeat cm	Plain
Vertical repeat cm	Plain
Composition	100% SOLUTION DYED ACRYLIC
Weight	500 gr/m²
Thickness (mm)	

Cleaning Instructions



Use Code

- Upholstery
- Accessories
- Curtains
- Outdoor / Indoor
- Nautic
- Contract

Environmental Standards

FR Standards

Finish

Water repellent

Anti-stain treatment

Optional Fabric Treatment

Waterproof/ Impermeable (Water Column: 1000 mm): Minimum one piece

Extra Softness + Martindale (Highter Resistance): Minimum one piece

Fireproof Treatment (UNE 1021 Parts 1-2/ IMO Pef 2010 Anex.1 Part 8/ BS5252 Cigarette & Match) : Minimum 500 meters


Warranty: 5 Years

The Agora warranty covers the fabric becoming unserviceable as a result of loss of colour or strength from normal exposure conditions, including sunlight, mildew, rot and atmospheric chemicals, when properly installed, used and maintained. The warranty does not cover labour and installation costs supplied by the dealer. The warranty neither applies against deterioration of any kind due to abusive use, accidental burns, negligence or perforations.

Waterproof and flame retardant treatments: Recommended for cushions and upholstery only. Always use the lamination face inside. Do not expose the coated side to sun or light.

Mechanical Performance

Abrasion Test / Martindale Rubs (EN ISO 12947-1,2)	15.000
Piling Test (EN ISO 12945-2)	4-5 / 5
Colour Fastness to light (ISO 105-B02-2)	7/8
Colour fastness to dry rub (EN ISO 105-X12)	4-5 / 5
Tearing strength (ISO 13934-1)	Warp: 300 N Weft: 300 N
Tensile Strenght (EN ISO 13934-1)	Warp: 1900 N Weft: 1200 N
Colour fastness to artificial weathering (ISO 105-B04)	4/5
Seam slippage (ISO 13936-2)	Warp: 5.0 mm Weft: 3.0 mm
Colour fastness to chlorinated water (ISO 105-E03)	5/5
Ultraviolet protection factor UPF (AZ/NZS 4399/1996)	50+
Spray test (ISO 24920)	4/5
Shrinkage to washing (ISO 5077:2007)	Warp: -1.5% Weft: 0%
Water column mm (ISO 20811)	60



Damaceno & Antunes
Rua da Alegria 387,
4475-310 Milheirós - Maia
+351229059160 info@damaceno-antunes.pt