

Design: VERSUS

BASIC INFORMATION

Brand	Bru	Number of colour ways	32
Tariff item number	5407920000	MID	CNTONFOR12
Country of origin	China	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	27
Full roll diameter inch	10.6	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains

Upholstery ✓

Accessories ✓

Curtains and draperies

Bed covering ✓

Maritime

Design: VERSUS

FABRIC SPECIFICATIONS

Composition	100% Polyester	Average yarn number	6.38
Construction	16.5x7.5	Woven	Yes
Useable width cm	1.46	Useable width inch	57.48
Full width cm	148	Full width inch	58.27
Weight g/m ²	376	Thickness mm	0.000
Colouring type	Yarn dyed	Filament or staple	60% textured + 40% not textured
Textured or non textured	60% filament + 40% staple		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emerised
Backing ✓	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment

Type of finish

Calender	Sanforized
Thermofixed ✓	Washed
Airo	Stenter

Type of print or dye

Disperse	Reactive
Vat ✓	Pigment

Weaving type

Plain	Twill ✓
Satin	Dobby
Jacquard	Pile
Other	

Design: VERSUS

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	Yes
FMVSS 302 Pass	Yes	NFPA 260	Yes

Design: VERSUS

MECHANICAL PERFORMANCE

Martindale rubs	100,000	Colour fastness to light	5
Wyzenbeek double rubs	200,000	Pilling	4
Brush pilling	4	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	5		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4-5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4-5		
Tearing strength - ISO 13937-3			
Tearing strength warp N	34	Tearing strength weft N	130
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	2000	Tensile strength weft N/5cm	350
Elongation - ISO 13934-1			
Elongation warp %	34	Elongation weft %	23
Seam slippage - ISO 13936-2			
Seam slippage warp mm	4	Seam slippage weft mm	4
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	-0.36	Dimensional change warp after ironing with steam	-0.20
Dimensional change warp after ironing without steam	0.00	Dimensional change weft	-0.31
Dimensional change weft after ironing with steam	-0.33	Dimensional change weft after ironing without steam	0.20

Design: VERSUS

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-2.83	Dimensional change warp after ironing	-2.86
Dimensional change weft	-0.77	Dimensional change weft after ironing	-0.67
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-6.89	Dimensional change warp after ironing	-6.72
Dimensional change weft	-2.73	Dimensional change weft after ironing	-2.46
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-5.02	Dimensional change warp after ironing	-1.39
Dimensional change weft	-1.59	Dimensional change weft after ironing	-1.39
Colour fastness ISO 105 D01	4-5		

Design: VERSUS

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	5.2 S
Weft Threads per cm	7.5	Weft TPM	NA

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	700D	Warp Textured	Yes
Warp Threads per cm	11	Warp TPM	NA

Yarn 3

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	1500D	Warp Textured	Yes
Warp Threads per cm	5.5	Warp TPM	NA

DOWNLOADS / CERTIFICATES

There are no technical details for this section.