

Design: ZONDA

BASIC INFORMATION

Brand	Bru	Number of colour ways	25
Tariff item number	5309119000	MID	INDDEHOM16
Country of origin	India	Characteristics	Flat Weave
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Face in	Yes	Full roll diameter cm	15
Full roll diameter inch	5.91	Average piece length m	50
Minimum for special colour m	1000	Delivery time weeks special lab dip	4

CARE AND USAGE

Care codes



Care code for bleaching

Do not bleach

Use codes

Curtains ✓
Upholstery
Accessories ✓

Curtains and draperies ✓
Bed covering
Maritime

Design: ZONDA

FABRIC SPECIFICATIONS

Composition	100% Linen	Average yarn number	26.93
Construction	20.47x20.47	Woven	Yes
Useable width cm	1.38	Useable width inch	54.33
Full width cm	140	Full width inch	55.12
Weight g/m ²	152	Thickness mm	0.350
Colouring type	Yarn dyed	Filament or staple	100% Staple
Textured or non textured	100% Not Textured		

Treatment

Bio treatment	Flame retardant
Soil and stain repellent	Brushed/emersed
Backing	Anti-bacterial/microbial
Mildew resistant	Odour resistant
Stain-free technology	PFC free
Other treatment	No treatment ✓

Type of finish

Calender	Sanforized ✓
Thermofixed	Washed
Airo	Stenter

Type of print or dye

Disperse	Reactive ✓
Vat	Pigment

Weaving type

Plain	Twill
Satin	Dobby ✓
Jacquard	Pile
Other	

Design: ZONDA

FABRIC TYPE

There are no technical details for this section.

ENVIRONMENTAL STANDARDS



FR STANDARDS

CAL 117 Complies	Yes	FMVSS 302 Pass	Yes
------------------	-----	----------------	-----

Design: ZONDA

MECHANICAL PERFORMANCE

Martindale rubs	5,000	Colour fastness to light	4
Wyzenbeek double rubs	5,000	Pilling	3
Brush pilling	3	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type unrated	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	4		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	5		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	33	Tearing strength weft N	42
Tensile strength - ISO 13934-1			
Tensile strength warp N/5cm	440	Tensile strength weft N/5cm	390
Elongation - ISO 13934-1			
Elongation warp %	12	Elongation weft %	9.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	5
Dimensional stability (indicated in %) - ISO 3759			
Dimensional change warp	0.26	Dimensional change warp after ironing with steam	1.39
Dimensional change warp after ironing without steam	-0.07	Dimensional change weft	-0.32
Dimensional change weft after ironing with steam	-0.13	Dimensional change weft after ironing without steam	0.07

Design: ZONDA

WASHABILITY

Resistance to domestic washing 30° C, indicated in % - ISO 6330

Dimensional change warp	-0.89	Dimensional change warp after ironing	-1.59
Dimensional change weft	-0.76	Dimensional change weft after ironing	-0.53
Colour fastness ISO 105 C06	4-5		

Resistance to domestic washing 60°C, indicated in % - ISO 6330

Dimensional change warp	-4.55	Dimensional change warp after ironing	-4.69
Dimensional change weft	-4.31	Dimensional change weft after ironing	-3.78
Colour fastness ISO 105 C06	4-5		

Resistance to dry cleaning P, indicated in % - ISO 105 D01

Dimensional change warp	-0.43	Dimensional change warp after ironing	-0.59
Dimensional change weft	-0.59	Dimensional change weft after ironing	-0.59
Colour fastness ISO 105 D01	4-5		

CONSTRUCTION

Yarn 1

Warp Composition	100% Linen	Warp Is Not High Tenacity	Yes
Warp Is Staple	Yes	Warp Sizes	44/1 Lia Linen dyed
Warp Threads per cm	20.47	Warp TPM	0

Yarn 2

Weft Composition	100% Linen	Weft Is Not High Tenacity	Yes
Weft Is Staple	Yes	Weft Sizes	60 Lea Linen dyed
Weft Threads per cm	20.47	Weft TPM	0

Design: ZONDA

DOWNLOADS / CERTIFICATES

There are no technical details for this section.